

Superconducting proximity effect in topological insulator and superconductor hybrid structures

Jiannong Wang

Hui Li, Tong Zhou, Jun He, Huachen Zhang, Hong-Chao Liu, Kam Tuen Law

Department of Physics, the Hong Kong University of Science and Technology, Clear Water Bay, Hong Kong, China

Email_phjwang@ust.hk

Abstract

Superconducting proximity effect in topological insulator and superconductor hybrid structure has attracted intense attention in recent years in an effort to search for mysterious Majorana fermions in condensed matter systems. Here I report on the superconducting proximity effect in a $\text{Bi}_2\text{Se}_3/\text{NbSe}_2$ junction fabricated with an all-dry transfer method. Resulting from the highly transparent interface, two sharp resistance drops are observed at 7 K and 2 K, respectively, corresponding to the superconducting transition of NbSe_2 flake and the superconducting proximity effect induced superconductivity in Bi_2Se_3 flake. Experimentally measured differential conductance spectra exhibit a bias-independent conductance plateau in the vicinity of zero bias below 7 K. As temperatures further decrease a zero bias conductance peak emerges from the plateau and becomes more enhanced and sharpened at lower temperatures. Our numerically simulated differential conductance spectra reproduce the observed bias-independent conductance plateau and zero bias conductance peak and show that the superconducting proximity effect in topological surface states is much stronger than that in the bulk states of Bi_2Se_3 . The Superconducting proximity effect induced superconducting gap for the topological surface states of Bi_2Se_3 is comparable to that of NbSe_2 and gives rise to the observed bias-independent conductance plateau below 7 K. In contrast, the superconducting proximity effect induced superconducting gap for the bulk states of Bi_2Se_3 is an order of magnitude smaller than that of NbSe_2 and superconducting topological surface states. These weakly paired bulk states in Bi_2Se_3 give rise to the zero bias conductance peak below 2 K. Our study has clearly unveiled the different roles of topological surface states and bulk states in the superconducting proximity effect, clarified the physical origin of the induced features, and shined light on further investigation of superconducting proximity effect and Majorana fermion in topological insulator and superconductor hybrid structures.